



Icosit® 5530/5530 EG

PVC-Acryl Finishing Coat

Technical Data Sheet

DESCRIPTION

Icosit 5530/5530 EG is a one component, thixotropic, PVC-acryl finish coat for steel and galvanized surfaces.

USES

- * Maintenance coating for bridges, pipelines, masts, gates etc.
- * Duplex coating for new/weathered galvanized structures.
- * Maintenance coating for PVC cladding.

ADVANTAGES

- * High film thickness.
- * Excellent barrier protection.
- * Excellent adhesion direct to aluminium structures.
- * Does not require 'T' wash or etch primer primer when applied to new/weathered galvanized substrates.
- * Direct application to aluminium and PVC substrates.

Technical Data

Colour:	Available in a selection of RAL and BS4800 colours and tinted to suit customer requirements. Refer to Sika standard colour shade chart.		
Finish:	Eggshell		
Density (SG):			
Icosit 5530	1.3 kg/litre		
Icosit 5530 EG	1.4 kg/litre		
Volume solids:	50%		
Typical film thickness per coat:	75 - 85 microns dry 150 - 170 microns wet		
Application temperatures & humidity conditions:	+5°C minimum (substrate and ambient) +3°C (5°F) above the dew point		
Coverage:	6.6 m ² /litre @ 75 microns dft		
Method of Application:	Airless spray, brush or roller		
Drying times:	10°C	20°C	30°C
Touch dry (hours):	2	1	0.5
Overcoating:			
Min (hours)	-	5	3
Max (weeks)	-----	Indefinite	-----
No of coats:	2		
In accordance with ISO 12 944 Pt 5			
VOC:	434 g/litre		
Flashpoint:	23°C		
All above values are approximate.			

SURFACE PREPARATION

Coated surfaces:

Icosit 5530/5530 EG is an intermediate/finishing coat which should be applied over a sound, prepared, primed or coated surface.

Test areas in accordance with ISO 129 44 should be carried out to confirm compatibility and adhesion.

The surface to be coated should be dry and free from contaminants, such as dust, oil, grease, algal growth etc.

Galvanized surfaces:

Refer to **Sika®** Galvanized Steel Duplex Guidelines. Available on request.

MIXING

Stir thoroughly before use. DO NOT THIN.

APPLICATION

Airless spray: Typically 100 - 300 microns per coat wft on vertical surfaces

Tip range 0.38 - 0.45 mm (15 - 18 thou)
Output fluid pressure at tip
Min (141 kg/cm²) (2000 psi)

Brush: Typically 75 - 150 microns per coat wft on vertical surfaces

Roller: Typically 75 - 150 microns per coat wft on vertical surfaces

THINNING

DO NOT THIN. The material is designed to be thixotropic and is not intended to be brushed out as an alkyd or conventional decorative coating.

IMPORTANT CONSIDERATIONS

- * Colour shade may vary from colour cards.
- * Apply only to dry surfaces.
- * Do not apply during mist or fog conditions or when snow or rain is imminent.
- * Avoid condensation on the coating during the initial drying period.
- * Apply in ventilated areas
- * Apply a small test area for compatibility onto unknown existing coatings.

CLEANING OF EQUIPMENT

Use **Thinner C**. Hardened material may have to be mechanically removed.

PACKAGING

Refer to latest price list

CONSUMPTION

Approximately 6.6 m²/litre @ 75 microns dft. These figures do not allow for surface porosity, profile or wastage).

STORAGE AND SHELF LIFE

Minimum 24 months in sealed containers stored in dry warehouse conditions (+5°C - +25°C).



Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

Please consult our Technical Sales Department for further information

SIKA LIMITED

Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ

Tel: 01707 394444 Email: sika@uk.sika.com

Fax: 01707 329129 www.sika.com

