



Sikafloor[®] 220W

Water Based Epoxy Conductive Coating

Technical Data Sheet

DESCRIPTION

Sikafloor 220W is a two component water based epoxy resin coating of high electrostatic conductivity.

USES

- * As a highly conductive intermediate layer under all anti-static/conductive **Sikafloor** finishes.

ADVANTAGES

- * Solvent free.
- * Electrostatically conductive.
- * Easy application.
- * Fast drying and curing.
- * Low Ω value.
- * Excellent bond.
- * Durable.
- * Excellent coverage.

FLOOR COATING SYSTEM:

Primer: 1 - 2 x **Sikafloor 156/157**.

Anti-static layer: 1 x **Sikafloor 220W**.

Top coat: Any antistatic/conductive **Sikafloor** finish.

Material consumption: Approx 0.10 kg/m² per coat.

Technical Data (typical)

Colour:	Black		
Density (SG):	Approx 1.0 kg/litre		
Volume solids:	Approx 40%		
Application temperatures & humidity conditions:	+10°C min, +30°C max (Substrate and ambient) RH 80% max		
Substrate M.C. & RH:	≤4% by wt or ≤75% RH		
Electical resistance (RA):	10 ³ - 10 ⁴ Ohms		
Additional application information:	+10°C	+20°C	+30°C
Pot life:	2-2.5 hrs	1.5-2 hrs	0.5-1hr
Waiting time between coats:			
min	24 hrs	15 hrs	10 hrs
max	7 days	5 days	4 days
Final drying times:			
Foot traffic:	20 hrs	13 hrs	8 hrs

All above values are approximate.

SURFACE PREPARATION

The cementitious substrate should be sound and of sufficient compressive strength. (Min 25 N/ mm²). Minimum pull off strength 1.5 N/mm².

The surfaces must be dry and free of all contaminants eg oils, grease, surface treatments and coatings etc. The substrate must be prepared mechanically to achieve an open textured fine gripping surface, free of cement laitance. Weak concrete should be removed and surface defects such as blowholes and voids must be fully exposed.

All dust, loose and friable material must be completely removed from all surfaces before application of the coating preferably by brush and vacuum.

Repairs to cementitious substrate and filling of blowholes levelling of irregularities etc should be carried out using an appropriate product from the **SikaDur**[®], **Sikafloor**[®] or **SikaGard**[®] range of materials.

MIXING

Prior to mixing, stir component A (resin), add all of component B (Hardener) and mix both components thoroughly with a low speed electric stirrer (300 - 400 rpm) for a minimum of 3 minutes until a uniform mix has been achieved.

APPLICATION

Prior to application, confirm substrate moisture content and RH. If >4% by wt & >75% RH. **Sikafloor**[®] **EpoCem**[®] may be applied as a DPM system.

Fix conductor tapes/electrodes, if required, in accordance with designers anti-static electrode design.

Apply **Sikafloor 220W** to the primed tack free substrate and over tapes/electrodes by brush or roller.

IMPORTANT CONSIDERATIONS

- * Do not apply **Sikafloor 220W** on substrates in which significant vapour pressure may occur.
- * Do not blind underlying layers.
- * Always ensure good ventilation when using **Sikafloor 220W** in a confined space.
- * Freshly applied **Sikafloor 220W** should be protected from damp, condensation and water for at least 24 hours.
- * Avoid puddles on surface.
- * Do not exceed consumption rates.
- * Check electrical resistance of **Sikafloor 220W** after the required earth connection points have been installed and prior to the application of conductive/ anti-static top coat.

CLEANING EQUIPMENT

Use water. Hardened material may have to be mechanically removed.

PACKAGING

Refer to latest price list

CONSUMPTION

Approximately 0.10 kg/m² (These figures do not allow for surface porosity, profile or wastage).
Maximum yield per pack - refer to latest price list.

STORAGE AND SHELF LIFE

Minimum 1 year in sealed containers stored in dry warehouse conditions (+5°C - +25°C).

Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

Please consult our Technical Sales Department for further information

SIKA LIMITED

Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ

Tel: 01707 394444 Email: sika@uk.sika.com

Fax: 01707 329129 www.sika.com

